



Mild Steel & Low Alloy Steel Welding Filler Wire

Product: Swastik Weld 90SB-3 WIRE

AWS A5.28 ER 90SB-3

Typical Application:

2.25Cr-1%Mo Heat Resistance steels

Typical Chemical Composition of Wire (%)

C	Si	Mn	Cr	Mo
0.09	0.47	0.66	2.31	1.00

Typical Mechanical Properties of all- weld- metal

Y.P N/mm2 (kgf/mm2)	T.S N/mm2 (kgf/mm2)	El (%)	PWHT
550 (56)	670(68)	26	690°C x 1hr

Standard Sizes:

Diameters (mm) = 1.2, 1.6, 2.0, 2.40, 3.15

Packing:

Tig: In cut length of 1000mm in 5kgs boxes (size: 1.6, 2.0, 2.40, 3.15mm)

Mig: Continuous wire in 12.5kgs / 15kgs Plastic Spool (size: 0.80, 1.2mm)

Note: We can supply wires & fluxes to stringent specifications for welding of various materials:

Steels (Carbon, Carbon Manganese, Carbon – Moly, Low Alloy, High Tensile, Stainless),
Nickel, Aluminum, Copper & their alloys by TIG / MIG / MAG /SA Processe

Works: Gala No. 19, Syndicate Indl. Complex, Near Golani Naka, Near Bank of Maharashtra,
Wallive Road, Vasai (E), Dist. Thane - 401 208. **Email:** swastikweld@gmail.com,
Skype: kamal.mehta14, **Mobile:** +91 9321434296, www.jinikmarketing.com